

FloorPro Protect Dispersion Extra RM 782

Extra robust, high-gloss polymer coating with excellent coverage, adhesion, non-slip properties and abrasion resistance as well as increased resistance to alcohol and disinfectants.

pH 8.6
in concentrate



Properties

- Optimum value preservation of the floor covering
- Highly economical thanks to fast application and long maintenance intervals
- Extra high coverage with just one to two coats due to very high solids content
- High coverage even on absorbent and old, tired floors
- Very short drying time
- Extremely hard-wearing due to high abrasion resistance and impact resistance and high protection against smearing (e.g. heel marks)
- Increased resistance to alcohol and disinfectant
- Excellent adhesion to the floor covering
- For heavy-duty and high-traffic areas (e.g. workshop or industrial areas, hospitals, schools)
- Anti-slip according to DIN 51131 and DIN EN 13893 (depending on the floor covering)
- Easily polished
- Suitable for sports halls and multi-purpose halls, anti-slip in accordance with DIN V 18032-2:2001-04 (depending on the floor covering)

Usage options

- manual
- Single disc machines

Application areas

Building cleaning	Floor care
Nursing and retirement homes, doctor's surgeries	Floor care
Industry	Floor care
Municipal	Floor care
Retail	Floor care
Hotels, gastronomy, catering	Floor care

Technical data

Container sizes	Packaging unit	Part number
5 l	2 Piece(s)	6.295-816.0

Application

Coating

- The surface must be free from care film residues and dirt (pH 7-8.5). The surface must be dry.
- Tilting the container using a circular motion.
- Do not dilute or mix product with other products.
- Application quantity depending on absorbency and type of floor: 1st coat: about 25 - 45 ml/m², 2nd coat: about 20 - 30 ml/m². Yield depending on application quantity.
- Distribute product evenly, sparingly, quickly and overlapping (wet on wet) using a flat or articulated mop.
- Allow to dry completely between applications (about 30 minutes, depending on humidity and temperature).
- Repeat as necessary (1-2 coats recommended). Apply product crosswise.
- Walkable after fully dry (about 3 hours).
- Suitable for normal traffic after about 24 hours.
- Fully hardens after about 14 days.

Instructions for use

- Do not apply to water-sensitive surfaces.
- Do not apply to wood or unsealed parquet flooring.
- Carry out an adhesion test on factory treated floors.
- Store away from frost.
- Only store in original container between 5 and 30°C.
- Do not put product residues back in the container.
- Close the container immediately after use.
- Clean the cleaning machine after use.

Warnings and safety recommendations according to EC Directives

- Z 20 Contains tributoxylethyl phosphate. May cause allergic reactions.

Further information

- Material Safety Data Sheet (MSDS)
- Quick Start
- FIGR expertise (Forschungs- und Prüfinstitut für Facility Management GmbH)
- Expertise relating to anti-slip properties according to DIN 51131 and DIN EN 13893
- Expert report on slip resistance in accordance with DIN V 18032-2:2001-04

Dosage and yield

Contents	Cleaning method	Dosage	Yield
1000 ml	Coating	undiluted	15 - 25 m ²